

HE3747H is a thermoset, solvent-based acrylic resin.

Characteristics

It is used to prepare bicycle baking paint, metal baking paint, overprint varnish with amino resin.

Delivery form

75% in xylene/isobutanol;

Product specifications

Solid Content:	73.0–77.0%
Viscosity (25°C, NDJ rotational viscometer):	4.0-8.0 Pa.s
Color number	≅ 1# (Fe-Co)
Acid value	6.0-10.0 mgKOH/g
Appearance	clear and transparent

The following items are not required:

flash point	25°C
density (20°C)	0.99-1.03 g/ml

Principal properties

- High gloss and fullness;
- High solid content;
- Good adhesion;
- Good recoatability.

Applications

It is used to prepare bicycle baking paint, metal baking paint, overprint varnish.

Compatibility with resins and solvents

HE3657	+	HE3654	+	xylene	+	2-Butoxyethanol	+
HE1762	+	HE3659	+	trimethylbenzene	+	CAC	+
HE3746	+	HE5968	+	butyl acetate	+	isobutanol	+
HE3646	+	CYMEL 325	+	cyclohexanone	+	Methyl ethyl ketone	+

Note: + means soluble/miscible; ○ means partially soluble/partially miscible;

— means insoluble/incompatible.

Reference recipe

varnish		diluent	
HE3747H	55	PMA	35
HE1762	22	DAA	15
BYK306	0.2	butyl acetate	35
ADP	1	CAC	10
isobutanol	9.8	isobutanol	5
xylene	14		
PMA	5		

Storage guidelines

The resin should be stored indoors in original, unopened, undamaged container in a dry place at storage temperature no more than 30°C. Exposure to direct sunlight should be avoided.

Shelf life

Under above mentioned storage condition, the shelf life of the resin will be 365 days after production.

For more than 365 days, the goods are still owned by ZOHO Company, the company's QC can make the corresponding extension of the shelf life after testing qualified.

Material safety

This product data sheet only applies to the latest version of Material Safety Data Sheet. Any updates to safety-related information that are consistent with legal requirements will only be reflected in the safety data sheet, at the same time the Sheet will be updated and published. Information on current classification and labelling, application and process methods, and more safety-related data can be found in the latest Material Safety Data Sheet.